

# KOERDYM C

## Compression Molded NdFeB

| Table of Properties<br>Grade | (BH) max          |       | Br  |      | HcJ  |       | HcB  |      |
|------------------------------|-------------------|-------|-----|------|------|-------|------|------|
|                              | kJ/m <sup>3</sup> | MGOe  | mT  | G    | kA/m | Oe    | kA/m | Oe   |
| Koerdym C 60EP               | 60                | 7.54  | 600 | 6000 | 1100 | 13816 | 485  | 6100 |
| Koerdym C 61EP               | 61                | 7.7   | 605 | 6050 | 1190 | 14953 | 400  | 5000 |
| Koerdym C 63EP               | 63                | 7.91  | 610 | 6100 | 950  | 11932 | 410  | 5200 |
| Koerdym C 64EP               | 64                | 8.1   | 635 | 6350 | 1010 | 12691 | 485  | 6100 |
| Koerdym C 68EP               | 68                | 8.8   | 620 | 6200 | 670  | 8419  | 640  | 8000 |
| Koerdym C 80EP               | 80                | 10.05 | 700 | 7000 | 680  | 8545  | 455  | 5700 |
| Koerdym C 83EP               | 83                | 10.4  | 660 | 6600 | 760  | 9550  | 475  | 6000 |
| Koerdym C 86EP               | 86                | 10.8  | 710 | 7100 | 560  | 7037  | 400  | 5000 |

\*All values are typical