

KOEROX™ HI

Hybrid Injection Molded Ferrite/NdFeB

Table of Properties Grade	(BH) max		Br		HcJ		HcB	
	kJ/m ³	MGOe	mT	G	kA/m	Oe	kA/m	Oe
Koerox HI 19 PA	18.5	2.32	315	3150	280	3519	215	2702
Koerox HI 22 PA	22.4	2.81	345	3450	300	3770	220	2765
Koerox HI 28 PA	28.0	3.52	390	3900	320	4021	245	3079

*All values are typical