

KOEROX™ I

Injection Molded Ferrite

Table of Properties Grade	(BH) max		Br		HcJ		HcB	
	kJ/m ³	MGOe	mT	G	kA/m	Oe	kA/m	Oe
Koerox I 1/20 PA	1.7	0.21	103	1030	220	2765	70	880
Koerox I 2/20 PA	2.7	0.34	128	1280	220	2765	86	1081
Koerox I 5/22 PA	5.2	0.65	170	1700	220	2765	120	1508
Koerox I 6/22 PA	6.7	0.84	190	1900	220	2765	131	1646
Koerox I 9/22 PA	8.9	1.12	219	2190	220	2765	151	1898
Koerox I 9/30 PA	8.9	1.12	220	2200	300	3770	151	1898
Koerox I 10/22 PA	10.3	1.29	236	2360	220	2765	157	1973
Koerox I 12/23 PA	11.5	1.45	250	2500	230	2890	161	2023
Koerox I 13/24 PA	13.0	1.63	265	2650	235	2953	173	2174
Koerox I 14/24 PA	14.3	1.80	276	2760	230	2890	175	2199
Koerox I 8/20 PS	7.5	0.94	200	2000	195	2450	134	1684
Koerox I 8/29 PS	7.4	0.93	205	2050	300	3770	136	1709
Koerox I 9/18 PS	10.2	1.28	235	2350	180	2262	147	1847
Koerox I 11/18 PS	11.7	1.47	250	2500	167	2099	138	1734

*All values are typical