

# KOEROX™ S

## Sintered Hard-Ferrite

Table of Properties Grade	(BH) max		Br		HcJ		HcB	
	$\text{kJ/m}^3$	MGOe	mT	G	kA/m	Oe	kA/m	Oe
Koerox S 100	9	1.31	230	2300	290	3644	155	1948
Koerox S 150	12	1.51	270	2700	290	3644	175	2199
Koerox S 300	24	3.02	365	3650	240	3016	210	2639
Koerox S 310	25	3.14	370	3700	270	3393	250	3142
Koerox S 320	28	3.52	390	3900	250	3142	240	3016
Koerox S 330	26	3.27	370	3700	260	3267	240	3016
Koerox S 350	29	3.64	390	3900	310	3896	270	3393
Koerox S 360	30	3.77	400	4000	175	2199	170	2136
Koerox S 400	31	3.90	400	4000	260	3267	255	3204
Koerox S 420	34	4.27	420	4200	270	3393	265	3330

\*All values are typical