

KOERZIT™ S

Sintered AlNiCo

Table of Properties Grade	(BH) max		Br		HcJ		HcB	
	kJ/m ³	MGOe	mT	G	kA/m	Oe	kA/m	Oe
Koerzit S 130	10.3	1.3	550	5500	57	716	54	679
Koerzit S 160	13.5	1.7	650	6500	60	754	57	716
Koerzit S 190	16.7	2.1	750	7500	62	57	60	754
Koerzit S 260	22.3	2.8	640	6400	114	1433	105	1319
Koerzit S 400	31.8	4.0	1100	11000	65	817	64	804
Koerzit S 500	41.4	5.2	1240	12400	51	641	51	641
Koerzit S 450	43.8	5.5	880	8800	119	1495	115	1445
Koerzit S 1800	43.8	5.5	740	7400	160	2011	150	1885

*All values are typical